

## TECHNICAL SHEET 04.01.19-GBR DECORATIVE TREATMENT OF INTERIOR SURFACES

# DECOR Cashmere

Decorative coating for interior surfaces

### 1. Description, Application

DECOR Cashmere is a decorative finishing coating which is not toxic, and it doesn't tend to yellow. It is characterized by good water vapour permeability, high resistance to fungi and bacteria and a pleasant smell during application. Thanks to its fine finishing coat, DECOR Cashmere can be used also in public facilities (hotels, restaurants, shops, etc.) and in prestigious ambiances in private houses. The product combines the characteristics of a Venetian stucco with original elegance, softness and light effects typical for antiquity wall textiles. DECOR Cashmere enables exceptional results (so far not seen for traditional paints) with the use of decorative capabilities and painter's creativity who can create original iridescences with each type of application suitable for every ambiance.

### 2. Packaging and Colour Shades

Plastic pots: 0.65 l

It is tinted at the JUMIX system, in colour shades according to the DECOR Cashmere colour chart.

### 3. Technical Data

Density (kg/dm <sup>3</sup> )		1,300 (±5%)
Drying time <2 T = +20 °C, rel. air humidity = 65 % (hours)	Touch dry	2 h
	Completely dry	24 h

Main ingredients: acrylic adhesive, mice fillers, additives, pigments

### 4. Surface Preparation

Surface should be solid, dry and clean, without any badly adhered particles, dust, remains of panelling oils, fat linings or other filth.

If uneven parts exist, the substrate must be additionally rendered and well levelled.

In normal conditions (T = +20 °C, relative air humidity = 65 %), dry or mature the newly applied renders and levelling compounds for at least a day for each mm of their thickness. Dry concrete surfaces for at least a month. Remove all paint coats that soak easily and quickly in water and coatings of oil paints, varnishes and enamels from the already painted surfaces. Prior to painting, it is obligatory to disinfect surfaces infected with wall mould

### 5. Preparation

Prior to use, DECOR Cashmere is only stirred well manually.



## 6. Application of Technique

The application of DECOR Cashmere is possible only in suitable conditions or suitable microclimate conditions: the temperature of the air and the wall surface should be between +5° C and +35° C and the relative air humidity should be below 80 %

### DECOR Cashmere –**Charm** technique

Preparation of substrate: The substrate, DECOR Primer smooth, is applied by using a roller, brush or an airless device. Let it dry for 4-5 hours.

Application of decorative technique: DECOR Cashmere is tinted into a desired colour shade at Jumix. By using plastic trowel, the decorative technique is applied in all directions. Let it dry for 6-8 hours. Apply decorative technique in the second coat in the same way as in the first coat. When the material starts to adhere to the substrate, smooth it by using a trowel (as when writing number eight).

### DECOR Cashmere – **Moonlight** technique

Preparation of substrate: The substrate, DECOR Primer smooth, is applied by using a roller, brush or an airless device. Let it dry for 4-5 hours.

Application of decorative technique: DECOR Cashmere is tinted into a desired colour shade. By using plastic trowel, the decorative technique is applied in all directions. Let it dry for 6-8 hours. DECOR Cashmere is applied in a second coat so that by using a plastic trowel the decorative render finish is applied unevenly onto already dried first coat. When the coat starts to adhere to the substrate, smooth it by using a trowel.

Approximate or average consumption for a 1-coat application:

DECOR Cashmere 220 - 250 ml/m<sup>2</sup> depending on absorption and roughness of the surface

## 7. Tool Cleaning, Waste Management

Thoroughly clean the tools with water immediately after use.

Keep unused primer (only the one that has not been diluted!) in a well-sealed packaging for potential repairs or later use. Waste liquid remains must not be emptied into drains, watercourses, or environment and they must not be disposed together with domestic wastes. Mix them with cement (hardened mortar remains and wastes, sand or sawdust may be added to them) and when they harden, deposit them onto the dumping grounds of construction waste (waste classification number: 17 09 04) or municipal waste (waste classification number: 08 01 12).

Cleaned packaging can be recycled

## 8. Safety and Health at Work

Further instructions regarding handling the product, use of personal protection equipment, waste management, tool cleaning, first aid measures, warning signs, signal words, components determining hazard, hazard statements and safety statements are listed in the product's safety sheet which you can find on [www.jub.rs](http://www.jub.rs) or you can require it from the manufacturer or seller.

When applying the product, the instructions and regulations regarding safety for construction, façade and painting works should also be observed.

## 9. Storage, Transportation Conditions and Durability

Storage and transportation at temperature +5° C to +25° C, protected from the direct sunlight, out of reach of children, MUST NOT FREEZE!

Shelf life when stored in an originally sealed and undamaged packaging: at least 24 months.

## 10. Quality Control

The product's quality characteristics are determined by the internal manufacturing specifications as well as by the local, European and other standards. JUB ensures achieving of the declared or set quality level by the ISO 9001 system for total quality management and control, which has been implemented at JUB for many years and which comprises daily quality checks in our own laboratories, occasionally at the Construction Institute in Ljubljana, at the Forschungsinstitut für Pigmente und Lacke in Stuttgart and at other independent expert institutions in Slovenia and abroad. During the manufacturing process, JUB strictly complies with the Slovene and European standards for the protection of the



environment and for ensuring security and health at work, which has been confirmed by the ISO 14001 and OHSAS 18001 certificates.

## 11. Other Information

Technical instructions contained in this brochure are provided based on our experience and are given as a guideline to achieve the optimum results. We shall not accept any responsibility for damage caused by incorrect selection of a product, incorrect use or unprofessional work.

Tinted product may differ from the sample in the colour chart or from the approved sample. However, the total colour difference  $\Delta E_{2000}$  – it is determined in accordance with the ISO 7724/1-3 and with a mathematical model CIE DE2000 – does not exceed 1.5. In order to check the colour shade, a dry application of paint on a test surface is compared to a standard of the concerned shade. A colour shade of a paint made on the basis of other colour charts is the best possible approximation for JUB's product bases and tinting agents. Therefore, in such cases the total colour difference from the desired shade may be even higher than the value guaranteed above. A difference in colour shade, which is the result of unsuitable working conditions, of a product preparation technique, which differs from the one in this technical sheet, of failure to follow the equalisation rules, of the application of the product onto an unsuitably prepared, over or not enough absorbing surface, more or less coarse surface, or on a wet or not dried enough surface cannot be subject of complaint.

This technical sheet supplements and replaces all preceding editions. JUB reserves the right to change and supplement data in the future.

Denomination and date of publishing: R-SRB /ver.1/; 1 November 2019.

---

JUB d.o.o. Šimanovci

Dositejeva 32  
22310 Šimanovci, Serbia  
T: +381 22 40 99 99  
F: +381 22 40 99 95 E: jub.info@jub.rs www.jub.eu

